

Flowfast Quartz TR (160 mils)

A trowel-applied, wear resistant and fast cure MMA flooring system with a robust decorative quartz finish.



Fast Cure:

Accelerates cure time, providing a fully operational surface in just 60 minutes.



Slip Resistant:

Adjustable, positively textured profile to minimize slip risks in wet or damp areas.



Chemical Resistant:

Protects against acids, alkalis, caustic soda, salt solutions, oils, fats and santizers.



Decorative:

Available in vibrant quartz color mixes that can be matched to neighboring interiors.



UV Resistant:

Exhibits excellent UV color stability over time and will not become brittle with age.

Rococo

Standard Colors:



Spring Glen




Blueberry Ice





Kitchen Red

BS 7976-2	Dry: 80 Wet: 60		
IMPACT RESISTANCE:			
ISO 6272	2.2 lb weight > 70 in 4.4 lb weight > 59 in		
COMPRESSIVE STRENGTH	1 :		
ASTM C 579	11,600 psi		
BOND STRENGTH:			
Greater than cohesive strer > 220 psi	ngth of 3,0	000 psi co	ncrete,
TENSILE STRENGTH:			
ASTM C 307	2,900 psi		
FLEXURAL STRENGTH:			
ASTM C 580	4,350 psi		
ABRASION RESISTANCE:			
ASTM D 4060 CS 17 Wheel, 1000 cycles	0.085g loss		
TEMPERATURE RESISTAN	ICE:		
Continuous Exposure:	Up to 160°F		
VOC:	<50 g/l		
COEFFICIENT OF FRICTIO	N:		
ASTM D 2047	Exceeds ADA recommendations		
SPEED OF CURE:	32°F	70°F	90°F
Light Traffic	60 mins	45 mins	45 min
Full Traffic	90 mins	60 mins	60 min
Full Chemical Cure	120 mins	90 mins	90 min



Products Included In This System

Primer: Flowfast Standard Primer at

80 - 130 sq ft/gal Scatter Sand: 0.1 lbs/sq ft

Mortar*: Flowfast Standard Binder/Quartz at

24 sq ft/mix

Sealer: Flowfast Standard Sealer at 125 sq ft/gal

*Mortar consists of 1 gal of Flowfast Standard Binder and 2 gal of color quartz.

Additional primer and membrane options are available for damp surfaces, crack bridging and high movement.

Installation

Installation should be carried out by a Key Resin Company preferred contractor with a documented quality assurance note. Obtain details of our preferred contractor network from our customer service team or by enquiring through our website. Detailed application instructions are also available upon request.

Substrate Requirements

Concrete or screed substrate should have a minimum of 3,000 psi compressive strength, free from laitance, dust and other contamination. The substrate should be dry to ASTM requirements and free from excessive moisture vapor transmission.

Primer

Under certain conditions the porosity of the substrate can lead to soak in of the Flowfast Primer. Excessive soak in will result in uncured primer will affect the curing of all subsequent layers. In cases where excessive soak in is experienced, the substrate must be reprimed.

Technical Profile

The figures and test results shown overleaf are typical properties achieved in laboratory tests at 75°F and at 50% Relative Humidity.

Installation Odor

MMA flooring does exhibit a distinct odor in its wet state but is non-toxic and extremely low in VOCs. During installation this odor can be completely eliminated with the right ventilation program in place. Once cured the odor dissipates rapidly.

Environmental Health & Safety

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs and maintenance. Environmental and health considerations are controlled during manufacture and application of the products by Key Resin Company staff and fully trained application teams.

Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Warranty

Key Resin Company products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.

Disclaimer

Any recommendation or suggestion relating to the use of products manufactured by Key Resin Company, whether in its technical literature or in response to a specific inquiry, is based upon data believed to be reliable, however the products and information are intended for use by applicators having requisite skill and know-how in the industry and therefore it is for the applicator to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the applicator has done so at its sole discretion and risk.

[01/17/22] FlowResin



